

## Niax\* Catalyst EF-100

### Product Description

Niax catalyst EF-100 is an isocyanate reactive, tertiary amine catalyst used in the manufacture of polyurethane foams that exhibit selective “blowing” activity towards reaction of water and isocyanate.

### Key Features and Typical Benefits

- Non-fugitive amine catalyst due to presence of reactive OH group
- Strong blow reactivity and wide processing latitude
- Good foam physical properties comparable to those of a classic blowing catalyst such as Niax A-1 catalyst
- Reduced foam odor and emissions to aid in compliance with VDA 278 requirements

### Typical Physical Properties

Appearance	Clear Liquid
Specific gravity at 25 °C (g/cm <sup>3</sup> )	0.954
OH value (mg KOH/g)	295
Solubility in water	Soluble

Typical properties are average data and are not to be used as or to develop specifications.

### Potential Applications

Potential applications include:

- flexible slab-stock foams
- high resilience molded foams
- viscoelastic foams
- rigid open-celled foams for spray and packaging
- microcellular and integral skin

### Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

### Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at [www.momentive.com](http://www.momentive.com) or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

\*Niax is a trademark of Momentive Performance Materials Inc.

Niax catalyst EF-100

**Limitations**

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

**Contact Information**

Email

[commercial.services@momentive.com](mailto:commercial.services@momentive.com)

**Telephone**

**Americas**

+1 800 295 2392

+1 614 986 2495

**Latin America**

+55 11 4534 9660

**Europe, Middle East,  
Africa and India**

00800 4321 1000

+40 213 044229

**Asia Pacific**

**China**

800 820 0202

**Japan**

+81 276 20 6182

**All Other Countries**

+60 3 9206 1543

For literature and technical assistance, visit our website at: [www.momentive.com](http://www.momentive.com)

**DISCLAIMER:**

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

**\*Niax, Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.**



260 Hudson River Road Waterford,  
NY 12188 USA  
[momentive.com](http://momentive.com)