

SILCOOL® TIA350R 放熱接着剤

速硬化と高い熱伝導性

モメンティブの SILCOOL TIA350R 接着剤は 1 成分の加熱硬化型シリコーンで、速硬化性と優れた熱伝導性を有しています。熱に曝されると迅速に硬化し、さまざまな被着体にしっかりと接着します。また、熱対策が求められるダイアタッチやヒートシンク接着などの用途に最適です。

SILCOOL TIA350R の主な特徴と効果

- 優れた熱伝導性
- 低温で迅速に硬化する接着剤
- 使いやすい 1 成分型
- 電気絶縁性
- 多くの被着体にプライマーを用いず接着
- 金属を腐食しない

用途

- ダイとヒートスプレッダーの間の放熱材
- さまざまな熱源と熱分散装置の間に使用する接着剤

一般特性


14 T				
硬化前硬				
外観		灰色		
粘度 (23 °C)	Pa•s	67		
Cured Properties (30 min at 120°C)				
密度 (23°C)	g/cm ³	3.1		
熱伝導率1	W/m·K	3.5		
熱抵抗² (BLT:60 μ m)	mm²·K/W	24		

硬さ (Type A)		77
引張強さ	MPa	1.6
伸び	%	20
引張せん断接着強さ ³	MPa	1.0
体積抵抗率	MΩ·m	4.8x10 ⁶
絶縁破壊強さ	kV/mm	20

^{1:} 熱線法 2: レーザーフラッシュ法 3: Al/Al (lap shear)

標準データは平均値であり、規格としての使用、あるいは規格策定での使用には適しません。


BLT とアッセンブリ圧力



試驗方法:

試料 0.02ml を $10mm \times 10mm$ のシリコンチップ 2 枚で挟み、30 秒間一定の圧力を加えた後、加熱硬化させ、試料の厚みを測定

BLT と熱抵抗



取扱い上の注意および保管について

- (1)取扱い時には、保護眼鏡および必要に応じて保護手袋を着用してください。
- (2)局所排気装置を運転し、換気をよくして作業してください。
- (3)室温では、粘度が徐々に上昇しますので、0~10℃の冷蔵庫内に保管してください。なお、低温から室温に戻す際、結露しますので、室温に戻してから開栓してください。
- (4)子供の手の届かない所に保管してください。
- (5)水、硫黄、窒素化合物、有機金属塩、リン化合物等を含む表面では硬化しないことがありますので、ご注意ください。
- (6)その他の情報は、製品安全データシート(MSDS)をご参照ください。

消防法

非危険物。指定可燃物可燃性液体類に該当。

特許状況

本書のいかなる内容についても、関連特許が存在しないことを暗示したものと解釈してはならず、またいかなる特許についても、その権利者による許可なく、その特許が対象とする発明を実施するた

めの許可、誘因または推奨を構成するものと解釈してはなりません。

製品の安全性、取り扱いおよび保管製品

製品の安全情報、安全な取扱手順、個人用保護具(必要な場合)、緊急サービスの連絡先情報、および安全な保管に必要な条件については、最新の安全データシート(SDS)および製品ラベルで確認してください。SDS は www.momentive.comで入手するか、あるいは MPMの担当者にご依頼ください。他の素材を MPM 製品(例:プライマー)と合わせて使用する際は、追加的な注意が必要になる場合があります。他の素材の製造者による安全情報を読み、それに従ってください。

制限

お客様はモメンティブ・パフォーマンス・マテリアルズ製品を評価し、特定の用途に対する使用適合性をご自身で判断する必要があります。

お問合せ窓口

製品の価格、取り扱い状況およびご注文については、Momentive.com/Contact us/ CustomerService/からカスタマーサービスへご連絡ください。パンフレットおよび技術情報については、弊社ウェブサイトwww.momentive.comをご覧ください。

免責条項:

モメンティブ・パフォーマンス・マテリアルズならびにその子会社および関係会社(以下、総称して 「サプライヤー」といいます)の素材、製品およびサービスは、サプライヤーの標準販売条件に基づ き販売されています。この標準販売条件は、該当する販売代理店契約または販売契約に含まれて おり、注文確認書や請求書の裏面に印刷され、また要求に応じて提供可能です。本書に記載の情 報、推奨、または提言は、誠意をもって提供されていますが、サプライヤーは明示的にも黙示的に も、(i)本書に記載の結果が最終使用条件下でも得られること、および(ii)製品、素材、サービス、 推奨または提言に取り入れられている設計の有効性もしくは安全性について、いかなる保証もいた しません。サプライヤーの標準販売条件に定めのあるものを除き、サプライヤーおよびその代理人 は、本書に記載の素材、製品またはサービスの使用によって生じたいかなる損害に対しても責任 **を負わないものとします。**サプライヤーの素材、サービス、推奨、または提言が、ユーザー自身の特 定の使用目的に適しているか否かの判断については、各ユーザー自身が全面的に責任を負いま す。各ユーザーは、すべてのテストや分析を特定および実施して、サプライヤーの製品、素材、また はサービスが組み込まれている最終製品が安全であり、最終使用条件における使用に適している ことを確認する必要があります。サプライヤーの署名入りの書面による合意がない限り、本書もしく はその他の文書または口頭による推奨または提言は、サプライヤーの標準販売条件の規定または 本免責条項の変更、修正、優先、または権利放棄とはみなされないものとします。本書に含まれる 素材、製品、サービスまたは設計の使用可能性または使用提案に関するいかなる記載も、当該使 用または設計を対象とするサプライヤーの特許その他の知的財産権に基づくライセンスを付与する ことを意図してはおらず、あるいはライセンスの付与と解釈してはならず、また、何らかの特許その 他の知的財産権を侵害する素材、製品、サービスまたは設計の使用の提案を意図しておらず、ま

た使用提案として解釈してはなりません。

Momentive および Momentiveのロゴは、Momentive Performance Materials Inc.の商標です。

Contact Information

Email

commercial.services@momentive.com

Telephone			
Americas	Latin America	EMEAI- Europe, Middle	ASIA PACIFIC
		East, Africa & India	
+1 800 295 2392	Brazil	Europe	China
Toll free*	+55 11 4534 9650	+390510924300	800 820 0202
+704 805 6946	Direct Number	Direct number	Toll free
Direct Number			+86 21 3860 4892
			Direct number
*All American	Mexico	India, Middle East & Africa	Japan
countries	+52 55 2169 7670	+ 91 44 71212207	+81 3 5544 3111
	Direct Number	Direct number*	Direct number
		*All Middle Eastern	Korea
		countries, Africa, India,	+82 2 6201 4600

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR

ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

* SILCOOL は Momentive Performance Materials Inc. の商標です。

The use of the "TM" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.