
Product Data

-Silicone Release Agent- TSM6347

PRODUCT DESCRIPTION

TSM6347 Silicone Release Agent is a silicone emulsion of 1,000mm²/s dimethyl silicone fluid developed as a mold release agent. TSM6347 Silicone Release Agent may provide excellent dilution stability, lubricity, and easy release, and it is an excellent candidate to consider for use in Food package release of rubbers, plastics and papers.

KEY FEATURES AND TYPICAL BENEFITS

- ◆ Easy release
- ◆ Good lubricity
- ◆ Dilution stability

POTENTIAL APPLICATIONS

- ◆ Food package release of rubbers, plastics and papers.

TYPICAL PHYSICAL PROPERTIES

PROPERTIES	TYPICAL VALUE
Appearance	Milky white liquid
Specific gravity (25°C)	0.99
Active content %	37
Surfactant	Anionic
Base polymer	1,000mm ² /s dimethyl silicone fluid
Diluent	Water

Typical property data values should not be used as specifications.

GENERAL CONSIDERATIONS FOR USE

◆ DILUTION

- In general, dilute the product with water to 0.5-2%. Tap water can be used as a diluent; however, the continuous use of hard water may result in accumulation of scale inside the mold.
- If necessary, lower the hardness of water with ion-exchange resins or other methods.
- Mix the product well before dilution.

◆ Application

- Apply the diluted TSM6347 Silicone Release Agent onto the mold surface with spray, brush, sponge or cleaning cloth.
- Make sure the entire surface is uniformly coated. The use of spray is

recommended.

HANDLING AND SAFETY

- ◆ Wear eye protection and protective gloves as required while handling the product.
- ◆ Use the product in a well-ventilated area.

STORAGE

- ◆ Store in a dark, cool place out of direct sunlight.
- ◆ Keep out of the reach of the children.

PACKAGING

16kg Pail

Issued July. 2015

.....

FOR INDUSTRIAL USE ONLY

It is the responsibility of the user to determine the suitability of any Momentive Performance Materials Japan product for any intended application. NEVER USE ANY MOMENTIVE PERFORMANCE MATERIALS JAPAN PRODUCT FOR IMPLANTATION OR INJECTION INTO THE HUMAN BODY. Specifications are available by contacting Momentive Performance Materials Japan. Typical property data values should not be used as this catalog are subject to change without notice. No part of this data may be reproduced without the prior approval of Momentive Performance Materials Japan. specifications. Inasmuch as Momentive Performance Materials Japan LLC has no control over the use to which others may put the material, it does not guarantee that the same results as those described herein will be obtained. Each user of the material should make his own tests to determine the suitability of the material for his own particular use. Statements concerning possible or suggested uses of the materials described herein are not to be construed as constituting a license under any Momentive Performance Materials Japan patent covering use or as recommendations for use of such materials in the infringement of any patent. Material Safety Data Sheets are available upon request from Momentive Performance Materials Japan. The contents of



Momentive Performance Materials Japan LLC

<http://www.momentive.jp>

Technical Answer Center (Japan) : Phone: +81-276-20-6182
Tokyo Office : Phone: +81-3-5544-3111

FAX: +81-276-31-6259
FAX: +81-3-5544-3122

