Technical Data Sheet



Silquest™ VX-225

Silquest* VX-225

Description

Silquest VX-225 silane is an amino-functional oligosiloxane adhesion promoter that may be considered for use over a broad range of adhesives and sealants applications.

Key Features and Benefits

Silquest VX-225 silane can improve the performance of moisture curable hybrid sealants, room temperature vulcanization (RTV) silicones and polyurethane sealants, adhesives and coatings.

Silquest VX-225 silane not only acts as an adhesion promoter but can modify the physical properties of Hybrid and RTV sealants by increasing their elasticity, lowering modulus and decreasing residual surface tack of the final cured product. It can also help reduce yellowing in sealant formulations.

As such, the beneficial characteristics of Silquest VX-225 silane include:

- Multi amino functionality for improved adhesion especially under wet conditions
- Reduced VOCs of the final formulation vs typical amino silanes reduced hazardous air pollutants (HAPs) emissions
- Lower sealant viscosity to improve sealant application rate
- Lower sealant residual surface tack compared to typical amino silanes
- Improved elasticity and lower modulus of the cured sealant
- Reduced yellowing with outdoor exposure

Typical Physical Properties

| Appearance | Clear liquid |
|----------------------------------|--------------|
| Color Index (Gardner) | 1 |
| Density (g/ml) | 0.99 |
| Refractive Index (nD25°C) | 1.42 |
| Viscosity (mPas) | 20 |
| Boiling Point (@ 1.1013 hPa), °C | 266 |
| Flash Point (°C) | 80 |

Typical physical property values should not be used as specifications.

Potential Applications

Adhesion in Peel Performance of SPUR** prepolymer-based Sealant

The following sealant formulation was used to evaluate the performance characteristics of Silquest VX-225 silane.

| Ingredients | wt% |
|---|-------|
| SPUR ⁺ 1015 LM Prepolymer | 22.94 |
| Plasticizer (DIDP) | 18.35 |
| Moisture Scavenger (Silquest A-171* silane) | 0.34 |
| Calcium Carbonate | 55.05 |
| UV Stabilizers | 0.46 |
| Silica | 1.115 |
| Titanium Dioxide | 1.15 |
| Adhesion Promoter | 0.57 |
| Tin Catalyst | 0.03 |
| Total | 100 |

Product formulations are included as illustrative examples only. Momentive makes no representation or warranty of any kind with respect to any such formulations, including, without limitation, concerning the effi cacy or safety of any product manufactured using such formulations.

SPUR⁺ 1015 LM prepolymer is available from Momentive Performance Materials.

^{*}Silquest is a trademark of Momentive Performance Materials Inc.

The physical properties of one-part SPUR⁺ prepolymer-based sealant using Silquest VX-225 silane were evaluated using European test methods (ISO 34, 37, 868, 4578, 9046, 7389). The adhesion in peel was measured using ASTM method C 794.

The properties of SPUR⁺ prepolymer-based sealant using Silquest VX-225 silane as adhesion promoter are shown in the following table. Silquest VX-225 silane appeared to outperform Silquest A-1110 silane (aminopropyltrimethoxysilane) on glass, aluminum and concrete substrates.

| | Ac | Adhesion Promoter 0.57 wt% | | |
|---|-----------------|----------------------------|-----------------|--|
| Physical | Silquest A-1110 | | Silquest VX-225 | |
| Properties | Si | lane | Silane | |
| Tensile Strength (MPa) | 1.29 | | 1.23 | |
| Elongation at Break (%) | 381 | | 1023 | |
| Tensile Modulus at 100% (MPa) | 0.0 | 67 | 0.32 | |
| Shore A Hardness | 30 | .2 | 23.8 | |
| Substrate (CF = cohesive failure) | | | | |
| Aluminum | | 3.8/100%CF | 5.3/100%CF | |
| Glass | | 3.5/100%CF | 4.2/100%CF | |
| Dry Concrete (surface smooth and flat) | | 2.8/100%CF | 3.6/40%CF | |
| Dry Concrete (surface rough and porous) | | 2.9/100%CF | 5.3/100%CF | |

Note: Test data. Actual results may vary.

Patent Status

Standard copy to come

Product Safety, Handling and Storage
Standard copy to come
Limitations

^{*}Silquest, Silquest A-171 and SPUR+ are trademarks of Momentive Performance Materials Inc.

Standard copy to come

Contact Information

Email

commercial.services@momentive.com

| Americas Latin America EMEAI- Europe, Middle ASI | A PACIFIC |
|--|--------------|
| East, Africa & India | |
| +1 800 295 2392 Brazil Europe Chi | na |
| Toll free* +55 11 4534 9650 +390510924300 800 | 820 0202 |
| +704 805 6946 Direct Number Direct number Toll | free |
| Direct Number +86 | 21 3860 4892 |
| Dire | ect number |
| *All American Mexico India, Middle East & Jap | an |
| countries +52 55 2169 7670 Africa +81 | 3 5544 3111 |
| Direct Number + 91 44 71212207 Dire | ect number |
| Direct number* | |
| *All Middle Eastern Kor | ea |
| countries, Africa, India, +82 | 2 6201 4600 |

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED

HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE. SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*Silguest™ is a trademark of Momentive Performance Materials Inc.

The use of the "TM" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.