

SPUR+* 3040 Prepolymer



MARKETING BULLETIN

SILANES - ADHESIVES & SEALANTS ADDITIVES

SPUR+ 3040 prepolymer is an excellent candidate to consider as a binder for high strength adhesives requiring adhesion to a variety of substrates. The low viscosity of SPUR+ 3040 prepolymer has shown it to be easy to formulate and use for the manufacture of adhesives. Many applications have benefited from the excellent heat resistance of SPUR+ 3040 prepolymer in circumstances where thermal stability is required.

Key Features and Typical Benefits

- High strength with good elongation
- Thermal stability
- Low viscosity
- 100% reactive

Typical Physical Properties

Property	Value
Appearance	Clear to slightly hazy liquid
Color (Co)	Light yellow
Specific Gravity at 25 °C	1.014
Viscosity at 25 °C, cP	~10,000

Typical properties are average data and are not to be used as or to develop specifications.

Typical Physical Properties and Heat Resistance of SPUR+ 3040 Prepolymer

In a standard polymer test, the SPUR+ 3040 prepolymer was cured by 1% of Fomrez† UL-28 tin catalyst and 0.5% of Niax* silicone L-501 at 23 °C and 50% relative humidity for 10 days. To test heat resistance, the cured SPUR+ 3040 prepolymer sheet was placed in an oven at 120 °C for 3 days. The properties of the SPUR+ 3040 prepolymer before and after the heat aging are compared in the table below.

Property of SPUR+ 3040 prepolymer	Initial Value	Under 120 °C for 3 days
Tensile Strength	5.25 MPa	7.58 MPa
Modulus at 100%E	4.43 MPa	3.79 MPa
Elongation at Break	113%	201%
Hardness	47 Shore A	50 Shore A

Note: Test data. Actual results may vary.

SPUR+ 3040 prepolymer can be added to a SPUR+ 1015 prepolymer-based sealant formulation to improve heat resistance. In the example below, SPUR+ 3040 prepolymer was added to a SPUR+ 1015 prepolymer-based sealant; the cured product then survived heat aging at 120 °C for 8 days. The example sealant formulation and test results are shown in the tables below.

Example Formulation

Ingredients	(g)
SPUR+ 1015 prepolymer	66.70
SPUR+ 3040 prepolymer	33.30
CaCO ₃	111.11
TS 720 (fumed silica)	4.17
R-960 (TiO ₂ , colorant)	1.39
Silquest A-171* silane	1.94
Silquest* A-1120 silane	1.94
DIDP (plasticizer)	55.56
Tinuvin† 213	0.83
Tinuvin 662 LD	0.83
Fomrez† SUL-4	0.28
Total	278.06

Product formulations are included as illustrative examples only. Momentive makes no representation or warranty of any kind with respect to any such formulations, including, without limitation, concerning the efficacy or safety of any product manufactured using such formulations.

Test Results

Property	Initial Value	Under 120 °C for 8 days
Tensile Strength	2.5 MPa	2.2 MPa
Modulus at 100%E	0.94 MPa	0.86 MPa
Elongation at Break	327%	258%
Hardness	36 Shore A	30 Shore A

Note: Test data. Actual results may vary.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative.

For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Customer Service Centers

Worldwide

Email: commercial.services@momentive.com

Americas

+1 800 295 2392
+1 614 986 2495

**Europe, Middle East,
Africa and India**

00800 4321 1000
+40 213 044229

Asia Pacific

China
800 820 0202
+86 21 3860 4892

All Other Countries
+60 3 9206 1543

Japan
0120 975 400
+81 276 20 6182

Disclaimer

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.