

SilFORT™ PHC587C2 Clear Coat

Description

SilFORT* PHC587C2 clear coat is a non-yellowing siloxane resin coating, which provides improved protection against coating- and/or substrate-deterioration from weather and ultraviolet rays. It is particularly improved in its resistance to long term cracking as a function of UV exposure. As an acidic coating, it provides excellent productivity with its primerless adhesion to Polycarbonate, coupled with a curing at 130°C. The product complies to the ECE regulation for European forward lighting applications.

Key Features and Benefits


- Improved Long Term Crack Resistance
- UV-Resistance
- Primerless Adhesion to Polycarbonate
- Abrasion- & Scratch-Resistance
- Good Transparency
- Solvent- & Chemical Resistance
- Heat Resistance
- Single-Coat-Process

Typical Physical Properties

Property	Hard Coat values
Solids Content [% by weight]	1-Butanol, Isopropanol
Solvents	1.12
Flash Point Penske Martens (closed cup)	19.4°C
Density [g/cm ³] @ 25°C	0.875 – 0.995

pH	4.7 - 6.7
Kin. Viscosity [cSt] @ 25°C	7 – 16
Shelf Life (@ +2 to +10°C)	12 months from date of manufacturing in unopened container

Hard Coat on Polycarbonate (Film Thickness: 6-12 µm)

Water Immersion ²	> 250 hrs.
Taber Abrasion ¹	<10%  Haze

¹ Taber Abrader® with 500g load, CS10F, Gen. IV abrasion wheel, 500 cycles. haze % measured acc. to ASTM D1003. Higher haze indicates higher abrasion. Humidity during coating and Taber® wheel variability will affect final results.

² Temperature = 65°C.

Chemical- / Solvent-Resistance

- | | |
|---------------------------------|---------------------------|
| 10W30 Motor Oil | Power Steering Fluid |
| Ethylene Glycol Antifreeze | 0.1N Sulfuric Acid |
| Heavy Duty Brake Fluid (Glycol) | 0.1N Sodium Hydroxide |
| Windshield Washer Fluid | Auto Polishing Paste |
| Heavy Duty Detergent | Petrol or Leaded Gasoline |
| Diesel Fuel | Battery Acid |

Packaging

- 180 kg Drum (#119250)
- 25 kg Pail (#114072)

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-

the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Preparation from cold storage


Allow the product to return to room temperature in original container. When the coating reaches 15°C, gently mix it to re-constitute any material which may have separated. Solution should appear homogeneous at room temperature.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Processing Recommendations

General Requirements:

Coating area should be clean, dust-free (Class 10,000 or better, acc. to US fed. std. 209e or  class 7 acc. to ISO 14644-1), well-ventilated and with the relative humidity controlled to 40 ± 15%. If necessary, parts should be washed or wiped clean with isopropyl alcohol, a mild detergent solution and clean water rinse, or ultrasonic bath followed by a filtered-air blow off and a final ionized-air blow-off. Cleanliness is critical for the production of good parts. Coating solution should be filtered continuously or just prior to use through a 1.0 µm absolute gel filter, using a 3 to 5 µm pre-filter. electric or indirect gas-fired ovens with good temperature distribution and air exchange are recommended for cure.

SiIFORT* PHC587C2 Clear Coat

The hard coat can be applied to parts by dip, spray or flow coating methods. For spray applications and large-part flow coating, the product can be reduced with an appropriate solvent (e.g. IPA, 1-Butanol). Coating should be applied to result in a cured film thickness of 6-12 microns or thicker, depending on application. The coating should be allowed to dry at room temperature until tack free approximately 10 to 20 minutes. After the part reaches a temperature of 130°C, the product cures to an abrasion

resistant hard coat in ☎ 30 minutes. Particularly for flow coating applications, for best performance, it is favorable to maintain an acetic acid level of 4% to ideally maximum of 7% in the re-circulating solution.

Contact Information

Email

commercial.services@momentive.com

Telephone

Americas	Latin America	EMEAI- Europe, Middle East, Africa & India	ASIA PACIFIC
+1 800 295 2392	Brazil	Europe	China
Toll free*	+55 11 4534 9650	+390510924300	800 820 0202
+704 805 6946	Direct Number	Direct number	Toll free
Direct Number			+86 21 3860 4892
			Direct number
*All American countries	Mexico	India, Middle East & Africa	Japan
	+52 55 2169 7670	+ 91 44 71212207	+81 3 5544 3111
	Direct Number	Direct number*	Direct number
		*All Middle Eastern countries, Africa, India,	Korea
			+82 2 6201 4600

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN

IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*SilFORT™ is a trademark of Momentive Performance Materials Inc.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.