

## SilFORT™ UVHC3000K Clear Coat

### Product Description

SilFORT UVHC3000K clear coat is a clear, solvent-based, UV-curing coating typically used on polycarbonate parts to help protect against abrasion, chemical damage and degradation caused by ultraviolet radiation and weathering. It is an excellent candidate to consider for use on headlamp lenses for forward lighting, exterior/interior trim and PC-, SAN- or PMMA-sheets. It complies with the ECE automotive forward lighting regulations<sup>1</sup> and is AMECA listed for three years exposure in Florida and Arizona.

### Key Features and Typical Benefits

- Excellent optical clarity
- Excellent chemical resistance
- Easy-to-clean properties
- Excellent abrasion and mar resistance
- Good weathering performance

### Potential Applications

- Automotive forward headlight lenses
- Automotive interior components
- High performance sheets and films

### Typical Physical Properties

Property	Unit	Typical Value
Physical Form	–	Liquid

Appearance	–	Clear, slightly yellow
Solids Content	% by weight	approx. 45
Kinematic Viscosity (at 25 °C)	cSt	approx. 9
Density (at 25 °C)	g/cm <sup>3</sup>	approx. 1.02
Shelf Life <sup>2</sup>	Months	15

Typical properties are average data and are not to be used as or to develop specifications.

### General Considerations for Use

Application Method	Spray, flow, dip, roller coating, digital inkjet printing
Reducing Solvents	<ul style="list-style-type: none"> <li>• 1- Methoxy-2-Propanol (CAS#107-98-2)</li> <li>2-Butanol (CAS#78-92-2)</li> <li>• 2- Propanol (CAS#67-63-0)<sup>3</sup></li> </ul>
Relative Humidity (Application & Ambient Flash Off)	Max. 65%

1 Based on the requirements as of December 2021

2 From date of manufacture in original, unopened container

3 Other compatible solvents may be considered

Room Temperature Flash Off	20 – 30 °C for 1 – 3 minutes
Pre-heating	1.5 to 6 minutes to reach 65 – 95 °C part surface temperature <sup>4 5</sup>
Intermediate Cool Down	Optional
Typical UV-Cure	3 – 6 J/cm <sup>2</sup> UV-A (EIT Inc. Power Puck II Device) <sup>6 7</sup>
Recommended Hardcoat Thickness	8 – 16 µm
Recommended Thickness of Interpenetrating Layer	>1 µm <sup>8</sup>

4 Longer pre-heating times may be required when using convection heating instead of IR-heating

5 Modified, high heat resistant PC grades may require higher pre-heat temperatures

6 Use of un-doped, medium pressure mercury arc lamps or microwave powered Hg

lamps with > 80 W/cm power is recommended. Typical UV-irradiance is 0.2 to 0.6 W/cm<sup>2</sup>

7 For applications that mainly require chemical resistance against solvents such as ketones, SilFORT UVHC3000K clear coat may be cured at a lower UV-dosage (1.5 J/cm<sup>2</sup>)

8 Higher thickness of 2 µm up to 6 µm may further improve adhesion after harsh humidity cycles

For best results in applying clear coat, filter the coating solution by combining a 5 µm pre-filter, followed by a 1 µm absolute gel-filter.

To help ensure adequate UV-cure, work with the UV-lamp supplier to select UV-reflectors that are appropriate for the parts to be treated.

Do not expose the product to any source of visible white light prior to UV-cure. To help avoid exposure when white light is present, do not use semi-transparent pipework.

### Packaging

Currently available in:

25 kg Steel Pail with PE liner

180 kg Steel Drum with PE liner

### Contact Information

Email

[commercial.services@momentive.com](mailto:commercial.services@momentive.com)

### Telephone

<b>Americas</b>	<b>Latin America</b>	<b>EMEAI- Europe, Middle East, Africa &amp; India</b>	<b>ASIA PACIFIC</b>
+1 800 295 2392	<b>Brazil</b>	<b>Europe</b>	<b>China</b>
Toll free*	+55 11 4534 9650	+390510924300	800 820 0202
+704 805 6946	Direct Number	Direct number	Toll free
Direct Number			+86 21 3860 4892
			Direct number

*All American countries	<b>Mexico</b> +52 55 2169 7670 Direct Number	<b>India, Middle East &amp; Africa</b> + 91 44 71212207 Direct number*	<b>Japan</b> +81 3 5544 3111 Direct number
		<b>*All Middle Eastern countries, Africa, India,</b>	<b>Korea</b> +82 2 6201 4600

For literature and technical assistance, visit our website at: [www.momentive.com](http://www.momentive.com)

**DISCLAIMER:**

**THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.** Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier’s products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier’s standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product,

service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.